

	Type	L #	Hits	Search Text	DBs
1	BRS	L1	46	(transflective ADJ (layer or plate or film or sheet))	USPAT; EPO; JPO
2	BRS	L2	2	1 with ((silver or Ag) or (alumium or Al))	USPAT; EPO; JPO
3	BRS	L4	56	(transflect\$3 ADJ (layer or plate or film or sheet))	USPAT; EPO; JPO
4	BRS	L5	2	4 with ((silver or Ag) or (alumium or Al))	USPAT; EPO; JPO
5	BRS	L3	16	transflect\$3 with ((silver or Ag) or (alumium or Al))	USPAT; EPO; JPO
6	BRS	L6	0	transflect\$3 with ((silver or Ag) and (alumium or Al))	USPAT; EPO; JPO
7	BRS	L7	3	(semi?transmi\$6 or semi?reflect\$3 or transflect\$3) with ((silver or Ag) and (alumium or Al))	USPAT; EPO; JPO
8	BRS	L9	2	transflect\$3 with ((silver or Ag) and (aluminum or Al))	USPAT; EPO; JPO
9	BRS	L8	9	(semi?transmi\$6 or semi?reflect\$3 or transflect\$3) with ((silver or Ag) and (aluminum or Al))	USPAT; EPO; JPO
10	BRS	L10	22	transflect\$3 with ((silver or Ag) or (aluminum or Al))	USPAT; EPO; JPO
11	BRS	L11	3	transflect\$3 with acrylic	USPAT; EPO; JPO
12	BRS	L12	4	((silver or Ag) or (aluminum or Al)) ADJ transflect\$3	USPAT; EPO; JPO
13	BRS	L13	8	transflect\$3 same acrylic	USPAT; EPO; JPO
14	BRS	L14	884	349/113	USPAT; EPO; JPO
15	BRS	L15	55	reflect\$3 with opaque ADJ conduct\$3	USPAT; EPO; JPO
16	BRS	L16	0	14 and 15	USPAT; EPO; JPO
17	BRS	L17	82	reflect\$3 same opaque ADJ conduct\$3	USPAT; EPO; JPO
18	BRS	L18	0	17 and 14	USPAT; EPO; JPO
19	BRS	L19	1	reflect\$3 and opaque ADJ conduct\$3 and 14	USPAT; EPO; JPO
20	BRS	L20	71	transflect\$3 and acrylic	USPAT; EPO; JPO
21	BRS	L21	63	20 not 13	USPAT; EPO; JPO
22	BRS	L22	1	acrylic ADJ (semi?transmi\$6 or semi?reflect\$3 or transflect\$3)	USPAT; EPO; JPO

**BEST AVAILABLE COPY**

	Type	L #	Hits	Search Text	DBs
23	BRS	L23	4	((silver or Ag) or (aluminum or Al)) ADJ (semi?transmi\$6 or semi?reflect\$3 or transflect\$3)	USPAT; EPO; JPO
24	BRS	L24	4	((silver) or (aluminum)) ADJ (semitransmi\$6 or semireflect\$3 or transflect\$3)	USPAT; EPO; JPO
25	BRS	L25	3	((silver) or (aluminum)) ADJ ( transflect\$3)	USPAT; EPO; JPO
26	BRS	L26	10	(semi?transmi\$6 or semi?reflect\$3 or transflect\$3) with acrylic	USPAT; EPO; JPO

**BEST AVAILABLE COPY**